

Test report nr. 214-2/21

**Compliance to the current European and National legislation [Reg. (EU) N.10/2011 and further updates and modifications and DM IT 21.3.73 and further updates and modifications] of your samples of "Isothermal container Polibox®, made of expanded polypropylene (EPP) – black colour".**

### **SAMPLING**

All the tests were performed on an appropriate number of samples, as required by the technical standards adopted.

### **SAMPLE DESCRIPTION**

Isothermal container Polibox®, made of expanded polypropylene (EPP) – black colour

### **DETERMINATION AND TEST METHODS**

COMPLIANCE FOR FOOD CONTACT MATERIALS ACCORDING TO THE DM of 21.3.73 S.O. GU n° 104 of 20/04/73, Reg. (EU) N. 10/2011 OJEU L 12 of 15/01/01, Reg. (EU) N. 1282/2011 OJEU L 328/22 of 10/12/2011, Reg. (EU) N. 1183/2012 OJEU L 338/13 of 12/12/2012; Reg. (EU) N. 202/2014 OJEU L62 of 4/3/2014; Reg. (EU) 2015/174 OJEU L30/2 of 05/02/2015, Reg. (EU) 2016/1416 OJEU L 230 of 25/08/2016, Reg. (EU) 2017/752 OJEU L 113 of 28/04/2017, Reg. (EU) 2018/79 OJEU L 14 of 19/01/2018, Reg. (EU) 2018/213 OJEU L 41 of 14/02/2018, Reg (EU) 2018/831 OJEU L 140 of 06/06/2018, Reg (EU) 2019/37 OJEU L9 of 10/01/2019, Reg. (EU) 2019/1338 OJEU L 209 of 09/08/2019 and Reg. (EU) 2020/1245 OJEU L 288/1 of 3/09/2020.

### **1. Overall migration in aqueous solution of simulant 3 % acetic acid and of ethanol by immersion (LOQ: 1 mg/dm<sup>2</sup>)**

Method: Reg. (EU) n. 10/2011 OJEU L 12 of 15/01/2011 (All V) + Reg. (EU) 2016/1416 OJEU L 230 of 22/08/2016 + Reg. (EU) 2017/752 OJEU L 113 of 29/04/2017 + Reg. (EU) 2019/37 OJEU L9 of 10/01/2019 + UNI EN 1186-1:2003 + UNI EN 1186-3:2003.

The test was performed on the simulants coming from the first, second and third contact  
CONTACT SURFACE = 1 dm<sup>2</sup>; SIMULANT VOLUME = 250 ml

### **2. Screening analysis - Head Space GC-MS (evaluation of the volatile substances)**

Analysis for the search and quantification, in the samples, of critic organic volatiles substances or undesired, including Non-Intentionally Added Substances (NIAS), via HS-GC-MS, on the basis of the procedure included in the normative UNI EN 13628-2:2004.

### 3. Screening analysis –Solvent extraction and GC-MS analysis

Screening analysis for the search and quantification on the material of critical or undesired semi- and non-volatile organic compounds, including the Non-Intentionally Added Substances (NIAS) and eventual restricted substances (SML or QM) via GC-MS.

### 4. PRIMARY AROMATIC AMINES = sum

### 5. PRIMARY AROMATIC AMINES - LC-MS method for individual quantification

### 6. Specific Migrations of the Metals of the Annex II Reg. (EU) N. 10/2011 modified by Reg. (EU) 2020/1245 – simulant B

### 7. Residual content of the substances X5, communicated under non-disclosure agreement

### 8. Residual content of the substance X1, communicated under non-disclosure agreement

## CONCLUSIONS

On the basis of the analyses performed, the sample of "Isothermal container Polibox®, made of expanded polypropylene (EPP) – black colour" are in compliance with the current European and National legislation [DM IT 21.3.73 and further updates and modifications and Reg. (EU) N.10/2011 and further updates and modifications], with respect to the checked parameters.



RESPONSABILE UFFICIO QUALITA'

POLIBOX® S.r.l.  
Via Campo dei Fiori, 13  
28009 Vittuone (MI)  
P.A.N.A. / C.F. 12597310964  
SDI T04ZHR3

IL LEGALE RAPPRESENTANTE



**Test report nr. 214-2/21**

**Date:** March, 26<sup>th</sup> 2021

**Subject:** **Compliance to the current European and National legislation [Reg. (EU) N.10/2011 and further updates and modifications and DM IT 21.3.73 and further updates and modifications] of your samples of "Isothermal container Polibox ®, made of expanded polypropylene (EPP) – black colour".**

The analyses were performed by Pack Co. staff, with its own instrumentation, in collaboration with LATA S.r.l. laboratory in Milan, under the agreements existing between the two entities.

Below, after the CONCLUSIONS section, the results of the performed tests are reported.

## **CONCLUSIONS**

**On the basis of the analyses reported in the RESULTS section, your sample of “Isothermal container Polibox ®, made of expanded polypropylene (EPP) – black colour” are in compliance with the current European and National legislation [DM IT 21.3.73 and further updates and modifications and Reg. (EU) N.10/2011 and further updates and modifications], with respect to the checked parameters.**

## **GENERAL DATA**

- |  |                              |
|--|------------------------------|
| - Samples arrival date:                  | March, 10 <sup>th</sup> 2021 |
| - Reception date:                        | March, 10 <sup>th</sup> 2021 |
| - Analyses start date:                   | March, 10 <sup>th</sup> 2021 |
| - Analyses end date:                     | May, 26 <sup>th</sup> 2021   |
| <br>                                     |                              |
| - Deviations from the agreed procedures: | NO                           |

## **SAMPLING**

The initial sampling was performed by the client.

All the tests were performed on an appropriate number of samples, as required by the technical standards adopted.

## **DECLARATION**

This test report relates only to the tested items as received and it shall not be partially reproduced, if not under written approval by this laboratory.

The laboratory declines every responsibility relate to the information provided by the client, included in the present test report, and possibly influencing the validity of the results.

LOQ: Quantification Limit. It is the lowest analyte concentration that can be revealed with acceptable precision (repeatability) and accuracy in well specified conditions. A result expressed as “<LOQ” does not indicate the absence of the searched analyte in the examined sample.

U: Uncertainty. If not otherwise specified, the uncertainty is extended and has been calculated with a recovery factor  $k=2$  corresponding to a probability interval of about 95%, or as confidence range calculated at a level of probability of about 95%.

If not otherwise specified, every eventual declaration of compliance reported in the CONCLUSION section arises from the comparison of the obtained results with the legislative limits considering the measure uncertainty.

## **SAMPLE DESCRIPTION**

The following information are given by the client

**- Isothermal container Polibox ®, made of expanded polypropylene (EPP) – black colour**

## **DETERMINATION AND TEST METHODS**

**COMPLIANCE FOR FOOD CONTACT MATERIALS ACCORDING TO THE DM of 21.3.73 S.O. GU n° 104 of 20/04/73, Reg. (EU) N. 10/2011 OJEU L 12 of 15/01/01, Reg. (EU) N. 1282/2011 OJEU L 328/22 of 10/12/2011, Reg. (EU) N. 1183/2012 OJEU L 338/13 of 12/12/2012; Reg. (EU) N. 202/2014 OJEU L62 of 4/3/2014; Reg. (EU) 2015/174 OJEU L30/2 of 05/02/2015, Reg. (EU) 2016/1416 OJEU L 230 of 25/08/2016, Reg. (EU) 2017/752 OJEU L 113 of 28/04/2017, Reg. (EU) 2018/79 OJEU L 14 of 19/01/2018, Reg. (EU) 2018/213 OJEU L 41 of 14/02/2018, Reg (EU) 2018/831 OJEU L 140 of 06/06/2018, Reg (EU) 2019/37 OJEU L9 of 10/01/2019, Reg. (EU) 2019/1338 OJEU L 209 of 09/08/2019 and Reg. (EU) 2020/1245 OJEU L 288/1 of 3/09/2020.**

### **1. Overall migration in aqueous solution of simulant 3 % acetic acid and of ethanol by immersion (LOQ: 1 mg/dm<sup>2</sup>)**

Method: Reg. (EU) n. 10/2011 OJEU L 12 of 15/01/2011 (All V) + Reg. (EU) 2016/1416 OJEU L 230 of 22/08/2016 + Reg. (EU) 2017/752 OJEU L 113 of 29/04/2017 + Reg. (EU) 2019/37 OJEU L9 of 10/01/2019 + UNI EN 1186-1:2003 + UNI EN 1186-3:2003.

<b>Simulants</b>	<b>Contact conditions</b>	<b>Contact mode</b>
Acetic acid 3% (w/v) – B	4 hours at 100 °C – repeated	Immersion

The test was performed on the simulants coming from the first, second and third contact  
**CONTACT SURFACE = 1 dm<sup>2</sup>; SIMULANT VOLUME = 250 ml**

## 2. Screening analysis - Head Space GC-MS (evaluation of the volatile substances)

Analysis for the search and quantification, in the samples, of critic organic volatiles substances or undesired, including Non-Intentionally Added Substances (NIAS), via HS-GC-MS, on the basis of the procedure included in the normative UNI EN 13628-2:2004.

Three aliquots of sample of around 0.2 g, are transferred in hermetically closed 20 ml vials and conditioned for 30 minutes at 125°C. The sampling of the volatiles organic compounds is made by automatic HS-GC-MS instrumentation, operating as follow:

Agilent 7697A – Head Space autosampler  
Oven: 125°C for 30 minutes  
Transfer line: 140°C  
Injection volume: 1500 µl  
Agilent 7890B Gas-chromatograph  
Column Restek RTX-5MS 30 m x 0.25 mm x 1.0 µm  
Temperature program:  
T<sub>start</sub> 45 °C x 3 min  
Ramp to T<sub>1</sub> 50°C in 10°C/min  
Ramp to T<sub>2</sub> 150°C in 20°C/min  
Ramp to T<sub>3</sub> 300°C in 30°C/min  
T<sub>end</sub> 300°C for 11.5 min  
Total time: 25 minutes  
Injector temperature: 200°C  
Mode: split 10:1  
Carrier: helium constant flux 1 ml/min

Agilent 5977B Mass spectrometer  
Acquisition mode: SCAN  
Acquisition range:  
from 2.5 min with m/z from 33 to 250  
from 10 min with m/z from 33 to 350  
from 15 min with m/z from 33 to 500  
Delay: 2.5 min

Quantification made on the basis of the response of a specific migration of volatile substances.

LOQ: 0.1 mg/kg of material

### 3. Screening analysis –Solvent extraction and GC-MS analysis

Screening analysis for the search and quantification on the material of critical or undesired semi- and non-volatile organic compounds, including the Non-Intentionally Added Substances (NIAS) and eventual restricted substances (SML or QM) via GC-MS.

Three aliquots of sample of around 0.2 g, are extracted with 6 ml of a solution of ethyl acetate/n-hexane doped with Methyl Heptadecanoate as internal standard, in ultrasonic bath at 60°C for 16 hours followed by analysis with the following operative conditions:

GERSTEL MPS liquid autosampler  
Injection volume: 1.5 µl  
Agilent 7890A Gas chromatograph  
Agilent DB-5HT 15 m x 0.25 mm x 0.1 µm column  
Temperature program:  
T<sub>initial</sub> 100°C x 2 min  
Ramp to T<sub>1</sub> 130°C at 10°C/min  
Ramp to T<sub>2</sub> 190°C at 15 °C/min  
Ramp to T<sub>3</sub> 320°C at 20°C/min  
T<sub>final</sub> at 320°C for 7.5 min  
Total time: 25 minutes

Injector: mode Splitless  
Injector temperature: 290°C  
Valve opening after 0.3 min  
Carrier: constant flow helium at 1 ml/min  
Agilent 5975C Mass spectrometer  
Acquisition mode: SCAN  
Acquisition range:  
from 3 min with m/z from 33 to 300  
from 10 min with m/z from 33 to 550  
from 15 min with m/z from 33 to 700  
Solvent delay: 3 min

Semiquantitative evaluation on the basis of the response of the detector to the internal standard.

LOQ: 1 mg/kg of material

### 4. PRIMARY AROMATIC AMINES = sum

Determination of the specific migration of Primary Aromatic Amines via spectrophotometric analysis, in Simulant B, coming from the first contact described on paragraph 1.

Preparation of the contact by Pack Co., quantification of the specific migration by L.A.T.A. S.r.l. laboratory in Milan, under the agreement existing between the two entities.

The quantification of the primary aromatic amines is performed by a spectrophotometric method based on the formation of a chromophore complex of the amines through diazotization and copulation, followed by the concentration on solid phase column and elution of the coloured complex having the highest absorbance at 550 nm. For the quantification a calibration curve at 550 nm was prepared from a stock solution of Aniline Hydrochloride diluted so to obtain 0, 5, 10, 15, 20, 30, 40 and 60 ppb solutions of aniline hydrochloride in 100 ml of 3% acetic acid.

LOQ: 0.005 mg/kg of simulant (as sum of primary aromatic amines)

## **5. PRIMARY AROMATIC AMINES - LC-MS method for individual quantification**

The evaluation of the specific migration for the Primary Aromatic Amines (PAA) is made on the simulant B coming from the contact described in paragraph 1.

The amines listed in the Annex XVII, appendix 8, entry 43 of the Regulation (EC) No. 1907/2006.

The quantification of the specific migration is made following the Protocol A published in the document "EUR 24815 EN" of the Joint Research Centre Institute for Health and Consumer Protection.

LOQ: 0.002 mg/kg of Simulant

## **6. Specific Migrations of the Metals of the Annex II Reg. (EU) N. 10/2011 modified by Reg. (EU) 2020/1245 – simulant B**

Specific migration of the metals listed in the Annex II of the Reg. (EU) N. 10/2011 modified by Reg. (EU) 2020/1245 in the simulant B coming from the contact described in paragraph 1.

Preparation of the contact by Pack Co., quantification of the specific migration by LATA S.r.l. laboratory in Milan, under the agreement existing between the two entities.

LOQ: 0.005 mg/kg of simulant for all the elements, except for the Cadmium, whose LOQ is 0.001 mg/kg.

## 7. Residual content of the substances X5, communicated under non-disclosure agreement

The extraction solution from the test on paragraph 3. is analysed by HPLC-MS instrumentation, working as follows:

HPLC Agilent 1260 Infinity  
Raptor column C18 2.1 mm x 100 mm x 2.7 µm  
Injection volume: 5 µl  
Flow: 0.3 ml/min  
Column temperature: 30 °C  
Analysis total time: 13 minutes

Eluent:	0 min	7 min
Water + 0.1% Formic acid	70 %	30 %
Acetonitrile + 0.1% Formic acid	30 %	70 %

Massa spectrometer AGILENT 6120 SQ  
Mode SIM+

Quantitative evaluation on the basis of a calibration line made from known concentration of the searched substance.

LOQ: 0.5 mg/kg of material

## 8. Residual content of the substance X1, communicated under non-disclosure agreement

The extraction solution from the test on paragraph 3. is analysed by HPLC-MS instrumentation, working as follows:

HPLC Agilent 1260 Infinity  
Zorbax column SB-C18 2.1 mm x 100 mm x 2.7 µm  
Injection volume: 1 µl  
Flow: 0.4 ml/min  
Column temperature: 30 °C  
Analysis total time: 5 minutes

Eluent:	
Water + 0.1% Formic acid	99.5 %
Acetonitrile + 0.1% Formic acid	0.5 %

Massa spectrometer AGILENT 6120 SQ

Mode SIM+

Quantitative evaluation on the basis of a calibration line made from known concentration of the searched substance.

LOQ: 0.5 mg/kg of material

## **RESULTS**

### **1. Overall migration in aqueous solution of simulant 3 % acetic acid and of ethanol by immersion (LOQ: 1 mg/dm<sup>2</sup>)**

<b>Isothermal container Polibox ®, made of expanded polypropylene (EPP) – black colour</b>			
<b>Simulant:</b> B – acetic acid 3% (w/v)			
<b>Contact conditions:</b> 4 hours at 100°C - first contact			
<b>Unit of measure:</b> mg/dm <sup>2</sup>			
<b>Determined values</b>	<b>Average value</b>	<b>Expanded uncertainty (U)</b>	<b>Limit value [Reg. (EU) N. 10/2011]</b>
3.7	5.0	1.2	10±2
7.8			
3.3			

<b>Isothermal container Polibox ®. made of expanded polypropylene (EPP) – black colour</b>			
<b>Simulant:</b> B – acetic acid 3% (w/v)			
<b>Contact conditions:</b> 4 hours at 100°C - second contact			
<b>Unit of measure:</b> mg/dm <sup>2</sup>			
<b>Determined values</b>	<b>Average value</b>	<b>Expanded uncertainty (U)</b>	<b>Limit value [Reg. (EU) N. 10/2011]</b>
1.7	2.9	1.2	10±2
3.2			
3.9			

<b>Isothermal container Polibox ®. made of expanded polypropylene (EPP) – black colour</b>			
<b>Simulant:</b> B – acetic acid 3% (w/v)			
<b>Contact conditions:</b> 4 hours at 100°C - third contact			
<b>Unit of measure:</b> mg/dm <sup>2</sup>			
<b>Determined values</b>	<b>Average value</b>	<b>Expanded uncertainty (U)</b>	<b>Limit value [Reg. (EU) N. 10/2011]</b>
<1	1.1	<b>1.2</b>	10±2
<1			
1.2			

## 2. Screening analysis - Head Space GC-MS (evaluation of the volatile substances)

In the following table, the amounts of the substances revealed in the samples with the technique described above, are reported as average of the three determinations, in mg/kg of material, its standard deviation (s.d.) and percentage standard deviation (s.d.%):

	Volatiles 125°C 30 min	Isothermal container Polibox ®, made of expanded polypropylene (EPP) – black colour		
<b>RT min</b>	<b>COMPOUND</b>	<b>mg/kg</b>	<b>s.d.</b>	<b>s.d. %</b>
3.20	Acetic acid	0.86	0.043	5
11.10	Aldehyde C9-C10	0.37	0.036	10
12.3-14.7	Linear and branched hydrocarbons C14-C20	0.79	0.099	13

## 3. Screening analysis – extraction with solvent and GC-MS analysis

In the following table, the amounts of the substances revealed in the samples with the technique described above, are reported as average of the three determinations, in mg/kg of material, its standard deviation (s.d.) and percentage standard deviation (s.d.%):

	Non-Volatiles EA/C6	Isothermal container Polibox ®, made of expanded polypropylene (EPP) – black colour

RT min	COMPOUND	mg/kg	s.d.	s.d. %
12.90	CAS 82304-66-3	19	1,0	5
17.70	Hydrocarbon C26	20	---	---
18.30	Erucamide	43	2,15	5
20.40	Irgafos 168	570	45	8
20.90	Oxidized Irgafos 168	400	35	9

#### 4. PRIMARY AROMATIC AMINES = sum

<b>Isothermal container Polibox ®, made of expanded polypropylene (EPP) – black colour</b>			
<b>Simulant:</b> B - acetic acid 3% (w/v)			
<b>Contact conditions:</b> 4 hours at 100° C – first contact			
<b>Unit of measure:</b> mg/kg of Simulant			
<b>Determined values</b>	<b>Average value</b>	<b>Uncertainty</b>	<b>Limit value</b>
< 0.005	< 0.005	---	0.01
< 0.005			
< 0.005			

<b>Isothermal container Polibox ®. made of expanded polypropylene (EPP) – black colour</b>			
<b>Simulant:</b> B - acetic acid 3% (w/v)			
<b>Contact conditions:</b> 4 hours at 100° C – second contact			
<b>Unit of measure:</b> mg/kg of Simulant			
<b>Determined values</b>	<b>Average value</b>	<b>Uncertainty</b>	<b>Limit value</b>
< 0.005	< 0.005	---	0.01
< 0.005			
< 0.005			

<b>Isothermal container Polibox ®. made of expanded polypropylene (EPP) – black colour</b>			
<b>Simulant:</b> B - acetic acid 3% (w/v)			

<b>Contact conditions:</b> 4 hours at 100° C – third contact			
<b>Unit of measure:</b> mg/kg of Simulant			
<b>Determined values</b>	<b>Average value</b>	<b>Uncertainty</b>	<b>Limit value</b>
< 0.005	< 0.005	---	0.01
< 0.005			
< 0.005			

## 5. PRIMARY AROMATIC AMINES - LC-MS method for individual quantification

<b>Isothermal container Polibox ®, made of expanded polypropylene (EPP) – black colour</b>			
<b>Simulant:</b> B - acetic acid 3% (w/v)			
<b>Contact conditions:</b> 4 hours at 100° C – first contact			
<b>Unit of measure:</b> mg/kg of Simulant			
<b>Compound</b>	<b>Average value</b>	<b>Expanded uncertainty</b>	<b>SML</b>
<b>o-Toluidine</b>	< 0.002	---	0.002
<b>4-methyl-m-phenylenediamine</b>	< 0.002	---	0.002
<b>o-Anisidine</b>	< 0.002	---	0.002
<b>4-chloroaniline</b>	< 0.002	---	0.002
<b>2,4,5-trimethylaniline</b>	< 0.002	---	0.002
<b>6-methoxy-m-toluidine</b>	< 0.002	---	0.002
<b>4-amino-azobenzene</b>	< 0.002	---	0.002
<b>4-methoxy-m-phenylenediamine</b>	< 0.002	---	0.002
<b>4-chloro-o-toluidine</b>	< 0.002	---	0.002
<b>2-naphthyl-amine</b>	< 0.002	---	0.002
<b>5-nitro-o-toluidine</b>	< 0.002	---	0.002
<b>4-amino-biphenyl</b>	< 0.002	---	0.002
<b>Benzidine</b>	< 0.002	---	0.002
<b>4,4'-diaminodiphenylmethane</b>	< 0.002	---	0.002
<b>4,4'-oxydianiline</b>	< 0.002	---	0.002

<b>3,3'-dimethylbenzidine</b>	< 0.002	---	0.002
<b>4,4'-thiodianiline</b>	< 0.002	---	0.002
<b>o-amino-azotoluene</b>	< 0.002	---	0.002
<b>4,4'-methylenedi-o-toluidine</b>	< 0.002	---	0.002
<b>3,3'-dimethoxybenzidine</b>	< 0.002	---	0.002
<b>3,3'-dichlorobenzidine</b>	< 0.002	---	0.002
<b>4,4'-methylene-bis-(2-chloroaniline)</b>	< 0.002	---	0.002

<b>Isothermal container Polibox ®, made of expanded polypropylene (EPP) – black colour</b>			
<b>Simulant:</b> B - acetic acid 3% (w/v)			
<b>Contact conditions:</b> 4 hours at 100° C – second contact			
<b>Unit of measure:</b> mg/kg of Simulant			
<b>Compound</b>	<b>Average value</b>	<b>Expanded uncertainty</b>	<b>SML</b>
<b>o-Toluidine</b>	< 0.002	---	0.002
<b>4-methyl-m-phenylenediamine</b>	< 0.002	---	0.002
<b>o-Anisidine</b>	< 0.002	---	0.002
<b>4-chloroaniline</b>	< 0.002	---	0.002
<b>2,4,5-trimethylaniline</b>	< 0.002	---	0.002
<b>6-methoxy-m-toluidine</b>	< 0.002	---	0.002
<b>4-amino-azobenzene</b>	< 0.002	---	0.002
<b>4-methoxy-m-phenylenediamine</b>	< 0.002	---	0.002
<b>4-chloro-o-toluidine</b>	< 0.002	---	0.002
<b>2-naphthyl-amine</b>	< 0.002	---	0.002
<b>5-nitro-o-toluidine</b>	< 0.002	---	0.002
<b>4-amino-biphenyl</b>	< 0.002	---	0.002
<b>Benzidine</b>	< 0.002	---	0.002
<b>4,4'-diaminodiphenylmethane</b>	< 0.002	---	0.002
<b>4,4'-oxydianiline</b>	< 0.002	---	0.002
<b>3,3'-dimethylbenzidine</b>	< 0.002	---	0.002

<b>4,4'-thiodianiline</b>	< 0.002	---	0.002
<b>o-amino-azotoluene</b>	< 0.002	---	0.002
<b>4,4'-methylenedi-o-toluidine</b>	< 0.002	---	0.002
<b>3,3'-dimethoxybenzidine</b>	< 0.002	---	0.002
<b>3,3'-dichlorobenzidine</b>	< 0.002	---	0.002
<b>4,4'-methylene-bis-(2-chloroaniline)</b>	< 0.002	---	0.002

<b>Isothermal container Polibox ®, made of expanded polypropylene (EPP) – black colour</b>			
<b>Simulant: B - acetic acid 3% (w/v)</b>			
<b>Contact conditions: 4 hours at 100° C – third contact</b>			
<b>Unit of measure: mg/kg of Simulant</b>			
<b>Compound</b>	<b>Average value</b>	<b>Expanded uncertainty</b>	<b>SML</b>
<b>o-Toluidine</b>	< 0.002	---	0.002
<b>4-methyl-m-phenylenediamine</b>	< 0.002	---	0.002
<b>o-Anisidine</b>	< 0.002	---	0.002
<b>4-chloroaniline</b>	< 0.002	---	0.002
<b>2,4,5-trimethylaniline</b>	< 0.002	---	0.002
<b>6-methoxy-m-toluidine</b>	< 0.002	---	0.002
<b>4-amino-azobenzene</b>	< 0.002	---	0.002
<b>4-methoxy-m-phenylenediamine</b>	< 0.002	---	0.002
<b>4-chloro-o-toluidine</b>	< 0.002	---	0.002
<b>2-naphthyl-amine</b>	< 0.002	---	0.002
<b>5-nitro-o-toluidine</b>	< 0.002	---	0.002
<b>4-amino-biphenyl</b>	< 0.002	---	0.002
<b>Benzidine</b>	< 0.002	---	0.002
<b>4,4'-diaminodiphenylmethane</b>	< 0.002	---	0.002
<b>4,4'-oxydianiline</b>	< 0.002	---	0.002
<b>3,3'-dimethylbenzidine</b>	< 0.002	---	0.002

<b>4,4'-thiodianiline</b>	< 0.002	---	0.002
<b>o-amino-azotoluene</b>	< 0.002	---	0.002
<b>4,4'-methylenedi-o-toluidine</b>	< 0.002	---	0.002
<b>3,3'-dimethoxybenzidine</b>	< 0.002	---	0.002
<b>3,3'-dichlorobenzidine</b>	< 0.002	---	0.002
<b>4,4'-methylene-bis-(2-chloroaniline)</b>	< 0.002	---	0.002

**6. Specific Migrations of the Metals of the Annex II Reg. (EU) N. 10/2011 modified by Reg. (EU) 2020/1245 – simulant B**

<b>Isothermal container Polibox ®, made of expanded polypropylene (EPP) – black colour</b>			
<b>Simulant:</b> B – acetic acid 3% (w/v)			
<b>Contact conditions:</b> 4 hours at 100° C – first contact			
<b>Unit of measure:</b> mg/kg of simulant			
<b>Element</b>	<b>Average value</b>	<b>Expanded uncertainty</b>	<b>Limit value Reg. (EU) N. 10/2011 up to Reg. (EU) 2020/1245</b>
Aluminium	0.118	0.069	1
Antimony	< 0.005	---	0.04
Arsenic	< 0.005	---	0.01
Barium	< 0.005	---	1
Cadmium	< 0.001	---	0.002
Cobalt	< 0.005	---	0.05
Chromium	< 0.005	---	0.01 <sup>(1)</sup>
Europium	< 0.005	---	0.05
Iron	0.042	0.019	48
Gadolinium	< 0.005	---	0.05
Lanthanum	< 0.005	---	0.05
Lithium	< 0.005	---	0.6
Manganese	< 0.005	---	0.6
Mercury	< 0.005	---	0.01
Nickel	< 0.005	---	0.02
Lead	< 0.005	---	0.01
Copper	0.089	0.057	5

Terbium	< 0.005	---	0.05
Zinc	0.087	0.034	5

<b>Isothermal container Polibox ®, made of expanded polypropylene (EPP) – black colour</b>			
<b>Simulant:</b> B – acetic acid 3% (w/v)			
<b>Contact conditions:</b> 4 hours at 100° C – first contact			
<b>Unit of measure:</b> mg/kg of simulant			
<b>Element</b>	<b>Average value</b>	<b>Expanded uncertainty</b>	<b>Limit value Reg. (EU) N. 10/2011 up to Reg. (EU) 2020/1245</b>
Aluminium	0.077	0.034	1
Antimony	< 0.005	---	0.04
Arsenic	< 0.005	---	0.01
Barium	< 0.005	---	1
Cadmium	< 0.001	---	0.002
Cobalt	< 0.005	---	0.05
Chromium	< 0.005	---	0.01 <sup>(1)</sup>
Europium	< 0.005	---	0.05
Iron	0.008	0.003	48
Gadolinium	< 0.005	---	0.05
Lanthanum	< 0.005	---	0.05
Lithium	< 0.005	---	0.6
Manganese	< 0.005	---	0.6
Mercury	< 0.005	---	0.01
Nickel	< 0.005	---	0.02
Lead	< 0.005	---	0.01
Copper	0.018	0.008	5
Terbium	< 0.005	---	0.05
Zinc	0.025	0.021	5

**Isothermal container Polibox ®, made of expanded polypropylene (EPP) – black colour**

<b>Simulant:</b> B – acetic acid 3% (w/v)			
<b>Contact conditions:</b> 4 hours at 100° C – third contact			
<b>Unit of measure:</b> mg/kg of simulant			
<b>Element</b>	<b>Average value</b>	<b>Expanded uncertainty</b>	<b>Limit value Reg. (EU) N. 10/2011 up to Reg. (EU) 2020/1245</b>
Aluminium	0.037	0.046	1
Antimony	< 0.005	---	0.04
Arsenic	< 0.005	---	0.01
Barium	< 0.005	---	1
Cadmium	< 0.001	---	0.002
Cobalt	< 0.005	---	0.05
Chromium	< 0.005	---	0.01 <sup>(1)</sup>
Europium	< 0.005	---	0.05
Iron	< 0.005	---	48
Gadolinium	< 0.005	---	0.05
Lanthanum	< 0.005	---	0.05
Lithium	< 0.005	---	0.6
Manganese	< 0.005	---	0.6
Mercury	< 0.005	---	0.01
Nickel	< 0.005	---	0.02
Lead	< 0.005	---	0.01
Copper	0.008	0.001	5
Terbium	< 0.005	---	0.05
Zinc	0.017	0.012	5

- (1) The limit for Chromium is set to 0.01 unless it is possible to exclude the presence of Cr<sup>VI</sup>, in this case the limit is raised to 3.6 mg/kg of food or simulant.

## 8. Residual content of the substances X5, communicated under non-disclosure agreement

<b>Isothermal container Polibox ®, made of expanded polypropylene (EPP) – black colour</b>		
<b>Solvent:</b> Ethyl-acetate/n-hexane		
<b>Extraction conditions:</b> 60 °C in ultrasonic bath for 16 hours		
<b>Unit of measure:</b> mg/kg		
<b>Determined values</b>	<b>Average value</b>	<b>Uncertainty</b>
< 0.5	< 0,5	---
< 0.5		
< 0.5		

The residual content of the X5 substances is low enough to make the theoretical specific migration lower than the specific migration limit.


#### 9. Residual content of the substances X1, communicated under non-disclosure agreement

<b>Isothermal container Polibox ®, made of expanded polypropylene (EPP) – black colour</b>		
<b>Solvent:</b> Ethyl-acetate/n-hexane		
<b>Extraction conditions:</b> 60 °C in ultrasonic bath for 16 hours		
<b>Unit of measure:</b> mg/kg		
<b>Determined values</b>	<b>Average value</b>	<b>Uncertainty</b>
< 0.1	< 0,1	---
< 0.1		
< 0.1		

The residual content of the X5 substances is low enough to make the theoretical specific migration lower than the specific migration limit.

#### END OF THE TEST REPORT

**Made by:** **Francesca LOMASTRO – Pack Co. S.r.l.**  
Area responsible





Test Report nr. 214-2/21

March, 26<sup>th</sup> 2021

**Approved by:** Gianluigi VESTRUCCI – Pack Co. S.r.l.  
Laboratory manager